

IN THE CLAIMS

Please cancel claim 2. Please rewrite claim 1 as indicated.

1. (Currently Amended) A cathode-ray tube comprising an evacuated envelope having therein an electron gun for generating at least one electron beam, a faceplate panel having a luminescent screen with phosphor elements on an interior surface thereof, and a focus mask, wherein the focus mask includes a plurality of spaced-apart first conductive strands having an insulating material thereon, and a plurality of spaced-apart second conductive wires oriented substantially perpendicular to the plurality of spaced-apart first conductive strands, the plurality of spaced-apart second conductive wires being bonded to the insulating material, wherein the insulating material comprises a low porosity lead-zinc-borosilicate glass powder having a median particle size less than about 1  $\mu\text{m}$ .

[2]

(Cancelled)

3. (Original) The cathode-ray tube of claim 1 wherein the low porosity lead-zinc-borosilicate glass includes one or more transition metal oxides.
4. (Original) The cathode-ray tube of claim 3 wherein the one or more transition metal oxides are selected from the group consisting of iron oxide ( $\text{Fe}_2\text{O}_3$  and  $\text{Fe}_3\text{O}_4$ ), titanium oxide ( $\text{TiO}_2$ ), zinc oxide ( $\text{ZnO}$ ), molybdenum oxide ( $\text{MoO}_3$ ), chromium oxide ( $\text{Cr}_2\text{O}_3$ ), tin oxide ( $\text{SnO}_2$ ), nickel oxide ( $\text{NiO}$ ), and combinations thereof.
5. (Original) The cathode-ray tube of claim 3 wherein the one or more transition metal oxides in the low porosity lead-zinc-borosilicate glass have a weight % in a range of about 2 % by weight to about 12 % by weight.



Amendment  
Serial No. 09/741,537

Page 3

6. (Original) The cathode-ray tube of claim 3 wherein the low porosity lead-zinc-borosilicate glass is SCC-11, or a mixture of lead, zinc, boron, and silicon oxides melted together to form an SCC-11-like glass.

7. (Original) The cathode-ray tube of claim 3 wherein the one or more transition metal oxides are added to the lead-zinc-borosilicate glass either by premelting or by mixing them with a lead-zinc-borosilicate powder.

8-14. (Withdrawn)

RECEIVED  
APR 16 2003  
TECHNOLOGY CENTER 2200